

HTL Resin

HTL is a high performance engineering material with high strength, rigidity, and heat resistance, able to withstand temperatures up to 114°C. HTL enables high resolution features, making it suitable for a broad range of engineering and medical applications including those which require autoclave sterilization.



	Cured Parts	Standard	
Tensile Properties	TENSILE STRENGTH	57 MPa	ASTM D638
	ELASTIC MODULUS	3029 MPa	ASTM D638
	ELONGATION AT BREAK	3%	ASTM D638
Flexural Properties	FLEXURAL STRENGTH	112.9 MPa	ASTM D790
	FLEXURAL MODULUS	1.8 GPa	ASTM D790
Impact Properties	IMPACT STRENGTH	30 J/m	ASTM D256
Thermal Properties	CTE @ 60C	47.5 $\mu\text{m}/\text{m}/^\circ\text{C}$	-
	HDT @ 0.45 MPa	114.2 $^\circ\text{C}$	ASTM D648 - 07
	TG	172 $^\circ\text{C}$	ASTM D7028
General Properties	CONTACT ANGLE	45-60 $^\circ$	ASTM D7334
	WATER ABSORPTION (24h)	1.05%	ASTM D570
	DIELECTRIC CONSTANT (10 GHz)	3.45	-
	DF	0.0245	-
	HARDNESS	81 Shore D	ASTM D785
	VISCOSITY	85 cP	-
	STANDARD COLOR	Yellow trans / Black / Carbon black**	-
COMPATIBLE BMF SYSTEMS	P130, S130*, P140, S140*, S230, S240, P150	-	

¹ Final properties are dependent on print conditions post-processing operations, and part geometry.

² Test samples were UV cured and heat cured.

* Needs a micro vat.

** Carbon black is only available for use on P140, S140, S240